



Technical Data Sheet

BrazeTec 60/40



TD BT 0651 E.01

Standard

CU 301 acc. DIN EN 1044 (L-CuZn40 acc. DIN 8513)
B-Cu60Zn(Si) 875/895 acc. ISO 3677

Nominal composition in wt.-% Zn remainder; Cu 60; Si 0,3; Sn 0,1
Permitted impurities (weight-%):
Al 0,01; As 0,01; Bi 0,01; Cd 0,025; Fe 0,25; Pb 0,02; Sb 0,01; Total impurities without Fe 0,2

Technical data

Melting range	app. 875 - 890 °C (DIN EN 1044)
Working temperature	app. 900 °C
Density	app. 8,4 g/cm ³
Shear strength	150 - 300 MPa (cemented carbide/steel)
Elongation	app. 35%
Electrical Conductivity	app. 15,0 m/ Ωmm ²
Operating temperature of brazed joint	max. 300 °C (without loss in strength)

Standard delivery form*

Wire: 1,5 - 2,0 - 3,0 mm Ø
Rods: 1,5 - 2,0 - 3,0 mm Ø, 500 mm length
Preforms: rings, shaped parts, sections,

*Other delivery forms on request

Application

BrazeTec 60/40 is a brazing alloy with good flow characteristics. It can be used for brazing any steels, copper as well as for nickel and nickel based alloys.

In special cases BrazeTec 60/40 can be used for brazing cemented carbides.

It can be used for brazing with flame or induction brazing procedures.

Typical applications are found e.g. in automotive and in the electric and tool industry.

The information and statements contained herein are provided free of charge. They are believed to be accurate at the time of publication, but BrazeTec makes no warranty with respect thereto, including but not limited to any result to be obtained or the infringement of any proprietary rights. Use or application of such information or statements is at user's sole discretion, without any liability on the part of BrazeTec. Nothing herein shall be construed as a license of or recommendation for use which infringes upon any proprietary rights. All sales are subject to BrazeTec's General Conditions of Sale and Delivery.