

AS 35

SAW Wires

C-Mn and low-alloy steels

Classification

EN ISO 14171-A-S2

AWS A5.17: EM 12K

Chemical analysis (Typical values in %)

C	Mn	Si	P	S
0.1	1	0.12	≤0.025	≤0.025